

## TEST REPORT

Applicant: Qbi Globe INC.  
10F-3, No. 530, Yingcai Rd., West Dist.  
Taichung City 40360, Taiwan (R.O.C.)

Number : TWNH00097332

Issue Date : Mar 28, 2023

### Sample Description:

One (1) Group of Submitted Samples Said To Be :

Item Name	: Supermarket Adventures: Grocery Mission
Item No.	: 114
Quantity	: 1 Group
Vendor/Manufacturer	: U.JERRY'S CO., LTD.
Country of Origin	: Taiwan
Goods Exported To	: U.S.A, Europe, Japan, Korea
Date Sample Received	: Mar 01, 2023
Date Test Started	: Mar 01, 2023

### Test Conducted:

As requested by the applicant, for details please refer to attached pages.

### Conclusion:

Please see page two to three.

### Remarks:

- #1 = Results were transferred from report No. TWNH00096527 dated Dec 13, 2022.
- #2 = Results were transferred from report No. TWNH00097338 dated Mar 28, 2023.
- #3 = Results were transferred from report No. TWNH00097335 dated Mar 29, 2023.

Authorized By:  
On behalf of Intertek Testing Services  
Taiwan Limited

Matt Wang  
Director



Signed by:

Thomas Chou  
Manager



Page 1 of 12



## TEST REPORT

Number : TWNH00097332

Conclusion:

<u>Tested sample</u>	<u>Standard</u>	<u>Result</u>
Submitted Samples	Mechanical and physical properties — As per European standard on safety of toys EN 71 part 1: 2014 + A1 : 2018	Pass
	Flammability test — As per European standard on safety of toys EN 71 part 2 : 2011 + A1 : 2014	Pass
Tested Components of Submitted Samples	19 Toxic Element Migration Test — As per European standard on safety of toys EN 71-3: 2019+A1:2021	Pass
	Phthalates Content — As per annex XVII items 51 and items 52 of the REACH regulation (EC) No. 1907/2006 and its amendment (EU) 2018/2005	Pass
	Total Cadmium (Cd) Content — As per annex XVII item 23 of the REACH regulation (EC) No. 1907/2006	Pass

Authorized By:  
On behalf of Intertek Testing Services  
Taiwan Limited

Matt Wang  
Director



Signed by:

*Thomas Chou*

Thomas Chou  
Manager



Page 2 of 12



## TEST REPORT

Number : TWNH00097332

Note: The attention of the applicant is drawn to the need for the item to be labeled as below

- Toys made available on the market shall bear the CE marking. The CE marking shall be subject to the general principles set out in Article 30 of Regulation (EC) No 765/2008. The CE marking shall be affixed visibly, legibly and indelibly to the toy, to an affixed label or to the packaging. In the case of small toys and toys consisting of small parts, the CE marking may alternatively be affixed to a label or an accompanying leaflet. Where, in the case of toys sold in counter displays, that is not technically possible, and on condition that the counter display was originally used as packaging for the toy, the CE marking may be affixed to the counter display. Where the CE marking is not visible from outside the packaging, if any, it shall as a minimum be affixed to the packaging. Where specific legislation does not impose specific dimensions, the CE marking shall be at least 5 mm high.
- The manufacturer's name, registered trade name or registered trade mark and the address at which the manufacturer can be contacted shall be indicated on the toy or, where that is not possible, on its packaging or in a document accompanying the toy. This requirement applies also to the name and address etc. of any importer.
- Manufacturers shall ensure that their toys bear a type, batch, serial or model number or other element allowing their identification, or where the size or nature of the toy does not allow it, that the required information is provided on the packaging or in a document accompanying the toy.
- Manufacturers and importers shall ensure that the toy is accompanied by instructions and safety information in a language or languages easily understood by consumers, as determined by the Member State concerned.
- A Member State may, within its territory, stipulate that warnings and safety instructions shall be written in a language or languages easily understood by consumers, as determined by that Member State.

If this information is not fixed to the toy itself, it should be accompanied by a notice in advising the purchaser to retain it.

---

Authorized By:  
On behalf of Intertek Testing Services  
Taiwan Limited

Matt Wang  
Director



Signed by:

Thomas Chou  
Manager



Page 3 of 12



## TEST REPORT

Number : TWNH00097332

Test Conducted

### **1. Mechanical and Physical Properties**

As per European standard on safety of toys EN 71 part 1:2014 + A1 : 2018

Appropriate age group for testing : For ages over 2 years

<u>Clause</u>	<u>Testing item</u>	<u>Assessment</u>
4*	General requirements	P
5*	Toys intended for children under 36 months	P
6	Packaging	P
7*	Warnings, markings and instructions for use	P (See Note)

Remarks : P = Pass ; NA = Not applicable

\* = The following subclauses of the standard are found applicable :

- 1) 4.1 Material cleanliness
- 2) 4.7 Edges
- 3) 4.8 Points and metallic, wires
- 4) 4.20 Acoustics
- 5) 4.23 Magnets
- 6) 5.1 General requirements
- 7) 7.1 General

### **2. Flammability Test**

As per European standard on safety of toys EN 71 part 2 : 2011+ A1 : 2014.

<u>Clause</u>	<u>Testing item</u>	<u>Assessment</u>
4.1	General	
	— Cellulose nitrate	P
	— Pile surface	NA
	— Flammable gas and liquid	NA
4.2	Toys to be worn on the head (5.2/5.3/5.4)	NA
4.3	Toy disguise costumes and toys intended to be worn by a child in play (5.4)	NA
4.4	Toys intended to be entered by a child (5.4)	NA
4.5	Soft-filled toys(5.5)	NA

Remarks : P = Pass

NA = Not applicable



Page 4 of 12



## TEST REPORT

Number : TWNH00097332

Test Conducted

### 3. 19 Toxic Element Migration Test

As per EN 71-3:2019+A1:2021 and followed by Inductively Coupled Plasma-Optical Emission Spectrometer (ICP-OES) and Inductively Coupled Plasma Mass Spectrometer (ICP-MS).  
Further confirmation test was determined by High Performance Liquid Chromatography with Diode Array Detection (HPLC-DAD), Liquid Chromatography /Inductively Coupled Plasma Mass Spectrometer (LC/ICP-MS), and Gas Chromatography-Mass Spectrometer (GC-MS) when necessary.

Category III: Scraped-off toy material

Element	Result (mg/kg)				Detection limit (mg/kg)	Limit (mg/kg)
	(1)(#1)	(2)	(3)	(4)		
Aluminium (Al)	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III))	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	10	180000
Organic tin	ND	ND	ND	ND	3.0	12
Zinc (Zn)	ND	ND	ND	ND	100	46000



## TEST REPORT

Number : TWNH00097332

Test Conducted

### 3. 19 Toxic Element Migration Test

Element	Result (mg/kg)				Detection limit (mg/kg)	Limit (mg/kg)
	(5)	(6)(#3)	(7)	(8)(#3)		
Aluminium (Al)	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III))	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	10	180000
Organic tin	ND	ND	ND	ND	3.0	12
Zinc (Zn)	ND	ND	ND	ND	100	46000

Element	Result (mg/kg)				Detection limit (mg/kg)	Limit (mg/kg)
	(9)(#2)	(10)(#3)	(11)	(12)		
Aluminium (Al)	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III))	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	10	180000
Organic tin	ND	ND	ND	ND	3.0	12
Zinc (Zn)	ND	ND	ND	ND	100	46000



## TEST REPORT

Number : TWNH00097332

Test Conducted

### 3. 19 Toxic Element Migration Test

Element	Result (mg/kg)				Detection limit (mg/kg)	Limit (mg/kg)
	(13)	(14)(#2)	(15)(#2)	(16)(#1)		
Aluminium (Al)	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III))	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	10	180000
Organic tin	ND	ND	ND	ND	3.0	12
Zinc (Zn)	ND	ND	ND	ND	100	46000

Element	Result (mg/kg)					Detection limit (mg/kg)	Limit (mg/kg)
	(17) (#1)	(18) (#1)	(19) (#1)	(20) (#1)	(22) (#1)		
Aluminium (Al)	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III))	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	248	24	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	10	180000
Organic tin	ND	11.7	5.4	ND	ND	3.0	12
Zinc (Zn)	ND	ND	ND	ND	ND	100	46000

Remarks: ND = Not detected

- Unless test result was marked with "Δ", organic tin content was derived from migration tin (Sn) content.
- According to the annex F to EN 71-3: 2019+A1:2021, the content of chromium (III) from the migration solution was calculated through the formula: chromium (III) = total chromium – chromium(VI).



## TEST REPORT

Number : TWNH00097332

Test Conducted

### 4. Phthalates Content

By solvent extraction and determined by Gas Chromatography-Mass Spectrometer (GC-MS).

#### I. Entry 51 of Annex XVII to Regulation (EC) No 1907/2006:

Compound	(1/9)(#2)	(2/3/4)	Result (%) (5/7/11)	(6/8)(#3)	(10)(#3)	Limit (%)
Diethyl hexyl phthalate (DEHP)	ND	ND	ND	ND	ND	0.1
Dibutyl phthalate (DBP)	ND	ND	ND	ND	ND	0.1
Benzyl butyl phthalate (BBP)	ND	ND	ND	ND	ND	0.1
Diisobutyl phthalate (DIBP)	ND	ND	ND	ND	ND	0.1
Sum of DEHP, DBP, BBP & DIBP	ND	ND	ND	ND	ND	0.1

Compound	(12/13)	(14)(#2)	Result (%) (15/16)(#2)	(17)(#2)	(18)(#1)	Limit (%)
Diethyl hexyl phthalate (DEHP)	ND	ND	ND	ND	ND	0.1
Dibutyl phthalate (DBP)	ND	ND	ND	ND	ND	0.1
Benzyl butyl phthalate (BBP)	ND	ND	ND	ND	ND	0.1
Diisobutyl phthalate (DIBP)	ND	ND	ND	ND	ND	0.1
Sum of DEHP, DBP, BBP & DIBP	ND	ND	ND	ND	ND	0.1

Compound	(19)(#2)	Result (%) (20)(#1)	(21)(#1)	Limit (%)
Diethyl hexyl phthalate (DEHP)	ND	ND	ND	0.1
Dibutyl phthalate (DBP)	ND	ND	ND	0.1
Benzyl butyl phthalate (BBP)	ND	ND	ND	0.1
Diisobutyl phthalate (DIBP)	ND	ND	ND	0.1
Sum of DEHP, DBP, BBP & DIBP	ND	ND	ND	0.1

#### II. Entry 52 of Annex XVII to Regulation (EC) No 1907/2006:

Compound	(1/9)(#2)	(2/3/4)	Result (%) (5/7/11)	(6/8)(#3)	(10)(#3)	Limit (%)
Di-(iso-nonyl) phthalate (DINP)	ND	ND	ND	ND	ND	--
Di-(Iso-decyl) phthalate (DIDP)	ND	ND	ND	ND	ND	--
Di-(n-octyl) phthalate (DNOP)	ND	ND	ND	ND	ND	--
Sum of DINP, DIDP & DNOP	ND	ND	ND	ND	ND	0.1

Compound	(12/13)	(14)(#2)	Result (%) (15/16)(#2)	(17)(#2)	(18)(#1)	Limit (%)
Di-(iso-nonyl) phthalate (DINP)	ND	ND	ND	ND	ND	--
Di-(Iso-decyl) phthalate (DIDP)	ND	ND	ND	ND	ND	--
Di-(n-octyl) phthalate (DNOP)	ND	ND	ND	ND	ND	--
Sum of DINP, DIDP & DNOP	ND	ND	ND	ND	ND	0.1





## TEST REPORT

Number : TWNH00097332

Test Conducted

### 4. Phthalates Content

II. Entry 52 of Annex XVII to Regulation (EC) No 1907/2006:

<u>Compound</u>	<u>Result (%)</u>			<u>Limit (%)</u>
	<u>(19)(#2)</u>	<u>(20)(#1)</u>	<u>(21)(#1)</u>	
Di-(iso-nonyl) phthalate (DINP)	ND	ND	ND	--
Di-(Iso-decyl) phthalate (DIDP)	ND	ND	ND	--
Di-(n-octyl) phthalate (DNOP)	ND	ND	ND	--
Sum of DINP, DIDP & DNOP	ND	ND	ND	0.1

Remarks: % = Percentage based on weight of tested sample  
 ND = Not detected  
 Detection limit = 0.005% (for each compound)  
 The above limits are quoted from Annex XVII Items 51 and Items 52 of the REACH regulation (EC) No. 1907/2006 and its amendment (EU) 2018/2005.

### 5. Total Cadmium (Cd) Content

Acid digestion method was used and total cadmium content was determined by Inductively Coupled Plasma-Optical Emission Spectrometer (ICP-OES).

<u>Tested Component</u>	<u>Result (ppm)</u>	<u>Limit (ppm)</u>
(1/9)(#2)	ND	100
(2/3/4)	ND	100
(5/7/11)	ND	100
(6/8)(#3)	ND	100
(10)(#3)	ND	1000
(12/13)	ND	100
(14)(#2)	ND	100
(15/16)(#2)	ND	100
(17)(#2)	ND	100
(18)(#1)	ND	100
(19)(#2)	ND	1000
(20)(#1)	ND	1000
(21)(#1)	ND	1000

Limit:  
 Not detected for cadmium plating  
 100 ppm for all plastic materials, paint contain less than 10% zinc, brazing fillers & metal parts of jewelry  
 1000 ppm for recovered PVC, coatings & paint contain greater than 10% zinc

Remarks: ppm = Parts per million based on weight of tested sample = mg/kg  
 ND = Not detected  
 Detection limit = 5 ppm  
 Above limit was quoted according to annex XVII items 23 of the REACH regulation (EC) No. 1907/2006.



## TEST REPORT

Number : TWNH00097332

Tested Components:

- (1) White plastic frame
  - (2) Light red plastic block
  - (3) Yellow plastic block
  - (4) Teal green plastic block
  - (5) Purple plastic block
  - (6) Light grey plastic block
  - (7) Green plastic part
  - (8) Orange plastic block
  - (9) White plastic block
  - (10) Colorful coating on block
  - (11) Yellowish orange plastic part
  - (12) Green plastic car
  - (13) Blue plastic part
  - (14) Red plastic car
  - (15) Grey plastic base
  - (16) Black plastic tire
  - (17) Black soft plastic tire
  - (18) Colorful paper cover with film
  - (19) Lacquer on cover
  - (20) Black coating on coil
  - (21) Colorful coating on page
  - (22) White paper page with colorful coating
- 




## TEST REPORT

Number : TWNH00097332

Sample photo:



TWNH00097332



## TEST REPORT

Number : TWNH00097332

Sample photo:



End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-twn.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

**Reporting Statements of Conformity:** Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.



Page 12 of 12

