

TEST REPORT

Applicant: Qbi Globe INC.
10F-3, No. 530, Yingcai Rd., West Dist.
Taichung City 40360, Taiwan (R.O.C.)

Number : TWNH00102162

Issue Date : Sep 18, 2024

Sample Description:

One (1) Group of Submitted Samples Said To Be :

Item Name	: Beginner - Fantasy Puzzle (Rainbow Playground Series)
Item No.	: 130
Quantity	: 1 Group
Vendor/Manufacturer	: RICH EASY TECHNOLOGY ENTERPRISE CO., LTD.
Country of Origin	: Taiwan
Goods Exported To	: America, Europe, Japan, Korea
Date Sample Received	: Sep 09, 2024
Date Test Started	: Sep 09, 2024

Test Conducted:

As requested by the applicant, for details please refer to attached pages.

Conclusion:

Please see page two.

Remarks:

= Results were transferred from report No. TWNH00100997 dated May 15, 2024.

Authorized By:
On behalf of Intertek Testing Services
Taiwan Limited

Matt Wang
General Manager



Signed by:

Thomas Chou
Manager



Page 1 of 8



TEST REPORT

Number : TWNH00102162

Conclusion:

<u>Tested sample</u>	<u>Standard</u>	<u>Result</u>
Submitted Samples	Mechanical and physical properties — As per European standard on safety of toys EN 71 part 1: 2014 + A1 : 2018	Pass
	Flammability test — As per European standard on safety of toys EN 71 part 2: 2020	Pass
Tested Components of Submitted Samples	19 Toxic Element Migration Test — As per European standard on safety of toys EN 71-3: 2019+A1:2021	Pass (#)
	Phthalates Content — As per annex XVII items 51 and items 52 of the REACH regulation (EC) No. 1907/2006 and its amendment (EU) 2018/2005	Pass (#)
	Total Cadmium (Cd) Content — As per annex XVII item 23 of the REACH regulation (EC) No. 1907/2006	Pass (#)

Authorized By:
On behalf of Intertek Testing Services
Taiwan Limited

Matt Wang
General Manager



Signed by:

Thomas Chou

Thomas Chou
Manager



Page 2 of 8



TEST REPORT

Number : TWNH00102162

Test Conducted

1. Mechanical and Physical Properties

As per European standard on safety of toys EN 71 part 1:2014 + A1 : 2018

Appropriate age group for testing : For ages over 3 years

<u>Clause</u>	<u>Testing item</u>	<u>Assessment</u>
4*	General requirements	P
5	Toys intended for children under 36 months	NA
6	Packaging	NA
7*	Warnings, markings and instructions for use	P

Remarks : P = Pass ; NA = Not applicable
* = The following subclauses of the standard are found applicable :

- 1) 4.1 Material cleanliness
- 2) 4.7 Edges
- 3) 4.8 Points and metallic, wires
- 4) 4.20 Acoustics
- 5) 4.23 Magnets
- 6) 7.1 General
- 7) 7.2 Toys not intended for children under 36 months

2. Flammability Test

As per European standard on safety of toys EN 71 part 2 : 2020

<u>Clause</u>	<u>Testing item</u>	<u>Assessment</u>
4.1	General	
	— Cellulose nitrate	P
	— Highly flammable solids	P
	— Pile surface	NA
	— Flammable gases, extremely flammable liquids, highly flammable liquids, flammable liquids or flammable gels	NA
4.2	Toys to be worn on the head (5.2/5.3/5.4)	NA
4.3	Toy disguise costumes and toys intended to be worn by a child in play (5.4/5.5)	NA
4.4	Toys intended to be entered by a child (5.4)	NA
4.5	Soft-filled toys(5.5)	NA

Remarks : P = Pass
NA = Not applicable



Page 3 of 8



TEST REPORT

Number : TWNH00102162

Test Conducted

3. 19 Toxic Element Migration Test

As per EN 71-3:2019+A1:2021 and followed by Inductively Coupled Plasma-Optical Emission Spectrometer (ICP-OES) and Inductively Coupled Plasma Mass Spectrometer (ICP-MS).
Further confirmation test was determined by High Performance Liquid Chromatography with Diode Array Detection (HPLC-DAD), Liquid Chromatography /Inductively Coupled Plasma Mass Spectrometer (LC/ICP-MS), and Gas Chromatography-Mass Spectrometer (GC-MS) when necessary.

Category III: Scraped-off toy material

Element	Result (mg/kg)						Detection limit (mg/kg)	Limit (mg/kg)
	(1)	(2)	(3)	(4)	(5)	(6)		
Aluminium (Al)	ND	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III))	ND	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	ND	10	180000
Organic tin	ND	ND	ND	ND	ND	ND	3.0	12
Zinc (Zn)	ND	ND	ND	ND	ND	ND	100	46000



TEST REPORT

Number : TWNH00102162

Test Conducted

3. 19 Toxic Element Migration Test

Element	Result (mg/kg)						Detection limit (mg/kg)	Limit (mg/kg)
	(7)	(8)	(9)	(10)	(11)	(12)		
Aluminium (Al)	ND	ND	ND	ND	ND	ND	300	28130
Antimony (Sb)	ND	ND	ND	ND	ND	ND	10	560
Arsenic (As)	ND	ND	ND	ND	ND	ND	10	47
Barium (Ba)	ND	ND	ND	ND	ND	ND	10	18750
Boron (B)	ND	ND	ND	ND	ND	ND	50	15000
Cadmium (Cd)	ND	ND	ND	ND	ND	ND	5	17
Chromium (III) (Cr(III))	ND	ND	ND	ND	ND	ND	10	460
Chromium (VI) (Cr(VI))	ND	ND	ND	ND	ND	ND	0.025	0.053
Cobalt (Co)	ND	ND	ND	ND	ND	ND	10	130
Copper (Cu)	ND	ND	ND	ND	ND	ND	10	7700
Lead (Pb)	ND	ND	ND	ND	ND	ND	10	23
Manganese (Mn)	ND	ND	ND	ND	ND	ND	10	15000
Mercury (Hg)	ND	ND	ND	ND	ND	ND	10	94
Nickel (Ni)	ND	ND	ND	ND	ND	ND	10	930
Selenium (Se)	ND	ND	ND	ND	ND	ND	10	460
Strontium (Sr)	ND	ND	ND	ND	ND	ND	100	56000
Tin (Sn)	ND	ND	ND	ND	ND	ND	10	180000
Organic tin	ND	ND	ND	ND	ND	ND	3.0	12
Zinc (Zn)	ND	ND	ND	ND	ND	ND	100	46000

Remarks: ND = Not detected

- Unless test result was marked with "Δ", organic tin content was derived from migration tin (Sn) content.
- According to the annex F to EN 71-3: 2019+A1:2021, the content of chromium (III) from the migration solution was calculated through the formula: chromium (III) = total chromium – chromium(VI).



Page 5 of 8



TEST REPORT

Number : TWNH00102162

Test Conducted

4. Phthalates Content

By solvent extraction and determined by Gas Chromatography-Mass Spectrometer (GC-MS).

I. Entry 51 of Annex XVII to Regulation (EC) No 1907/2006:

<u>Compound</u>	<u>(1/3)</u>	<u>Result (%)</u> <u>(2/5)</u>	<u>(4)</u>	<u>Limit (%)</u>
Diethyl hexyl phthalate (DEHP)	ND	ND	ND	0.1
Dibutyl phthalate (DBP)	ND	ND	ND	0.1
Benzyl butyl phthalate (BBP)	ND	ND	ND	0.1
Diisobutyl phthalate (DIBP)	ND	ND	ND	0.1
Sum of DEHP, DBP, BBP & DIBP	ND	ND	ND	0.1

<u>Compound</u>	<u>(6/7/10)</u>	<u>Result (%)</u> <u>(8/9)</u>	<u>(11/12)</u>	<u>Limit (%)</u>
Diethyl hexyl phthalate (DEHP)	ND	ND	ND	0.1
Dibutyl phthalate (DBP)	ND	ND	ND	0.1
Benzyl butyl phthalate (BBP)	ND	ND	ND	0.1
Diisobutyl phthalate (DIBP)	ND	ND	ND	0.1
Sum of DEHP, DBP, BBP & DIBP	ND	ND	ND	0.1

II. Entry 52 of Annex XVII to Regulation (EC) No 1907/2006:

<u>Compound</u>	<u>(1/3)</u>	<u>Result (%)</u> <u>(2/5)</u>	<u>(4)</u>	<u>Limit (%)</u>
Di-(iso-nonyl) phthalate (DINP)	ND	ND	ND	--
Di-(Iso-decyl) phthalate (DIDP)	ND	ND	ND	--
Di-(n-octyl) phthalate (DNOP)	ND	ND	ND	--
Sum of DINP, DIDP & DNOP	ND	ND	ND	0.1

<u>Compound</u>	<u>(6/7/10)</u>	<u>Result (%)</u> <u>(8/9)</u>	<u>(11/12)</u>	<u>Limit (%)</u>
Di-(iso-nonyl) phthalate (DINP)	ND	ND	ND	--
Di-(Iso-decyl) phthalate (DIDP)	ND	ND	ND	--
Di-(n-octyl) phthalate (DNOP)	ND	ND	ND	--
Sum of DINP, DIDP & DNOP	ND	ND	ND	0.1

Remarks: % = Percentage based on weight of tested sample

ND = Not detected

Detection limit = 0.005% (for each compound)

The above limits are quoted from Annex XVII Items 51 and Items 52 of the REACH regulation (EC) No. 1907/2006 and its amendment (EU) 2018/2005.



TEST REPORT

Number : TWNH00102162

Test Conducted

5. Total Cadmium (Cd) Content

Acid digestion method was used and total cadmium content was determined by Inductively Coupled Plasma-Optical Emission Spectrometer (ICP-OES).

<u>Tested Component</u>	<u>Result (ppm)</u>	<u>Limit (ppm)</u>
(1/3)	ND	100
(2/5)	ND	100
(4)	ND	100
(6/7/10)	ND	100
(8/9)	ND	100
(11/12)	ND	100

Limit:

Not detected for cadmium plating

100 ppm for all plastic materials, paint contain less than 10% zinc, brazing fillers & metal parts of jewelry

1000 ppm for recovered PVC, coatings & paint contain greater than 10% zinc

Remarks: ppm = Parts per million based on weight of tested sample = mg/kg

ND = Not detected

Detection limit = 5 ppm

Above limit was quoted according to annex XVII items 23 of the REACH regulation (EC) No. 1907/2006.

Tested Components:

- (1) Black plastic wheel
- (2) Black plastic car
- (3) White plastic wheel
- (4) Black soft plastic tire
- (5) White plastic side
- (6) Red plastic block
- (7) Orange plastic block
- (8) Yellow plastic block
- (9) Teal plastic block
- (10) Aqua blue plastic block
- (11) Dark blue plastic block
- (12) Purple plastic block



Page 7 of 8







TEST REPORT

Number : TWNH00102162

Sample photo:

TWNH00102162



End of Report

Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our standard Terms and Conditions which can be obtained at our website: <http://www.intertek-twn.com/terms/>. Intertek's responsibility and liability are limited to the terms and conditions of the agreement.

This report is made solely on the basis of your instructions and / or information and materials supplied by you and provide no warranty on the tested sample(s) be truly representative of the sample source. The report is not intended to be a recommendation for any particular course of action, you are responsible for acting as you see fit on the basis of the report results. Intertek is under no obligation to refer to or report upon any facts or circumstances which are outside the specific instructions received and accepts no responsibility to any parties whatsoever, following the issue of the report, for any matters arising outside the agreed scope of the works. This report does not discharge or release you from your legal obligations and duties to any other person. You are the only one authorized to permit copying or distribution of this report (and then only in its entirety). Any such third parties to whom this report may be circulated rely on the content of the report solely at their own risk.

Reporting Statements of Conformity: Please note that the test results contain statement of conformity with the decision rules which are based on the specifications of customers, regulations and standards, and does not consider measurement uncertainty.



Page 8 of 8

